

AFRL Update on Status of Cr-Free Coating Systems

ASSETS Defense
29 August 2012



Mike Spicer AFRL/RXSSO 937-255-0942
mike.spicer@wpafb.af.mil



Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 29 AUG 2012		2. REPORT TYPE		3. DATES COVERED 00-00-2012 to 00-00-2012	
4. TITLE AND SUBTITLE AFRL Update on Status of Cr-Free Coating Systems				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Air Force Research Laboratory, AFRL/RXSSO, Wright Patterson AFB, OH, 45433				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES ASETSDefense 2012: Sustainable Surface Engineering for Aerospace and Defense Workshop, August 27-30, 2012, San Diego, CA. Sponsored by SERDP/ESTCP.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	18. NUMBER OF PAGES 27	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			



Presentation Outline



Public Affairs release # 88ABW-2008-0909

- **Approved Non-Chrome Coatings**
- **Issues with Non-Chrome Coating Systems**
 - **Unclear Requirement**
 - **Problems Developed**
 - **Non-Chrome not as Robust as Chrome**
 - **Lab Results don't Translate to Real World**
 - **Not All Aircraft are Created Equal**
- **AFRL Path Forward**
- **PreKote/Mg-Rich Coating System**
- **Current Field Testing**



USAF Approved Non-chrome Coatings



Public Affairs release # 88ABW-2008-0909

- **Authorized Non-chrome Pretreatments**

- PreKote approved – T.O. 1-1-8

Authorized for use
under a Chrome Primer

- **Qualified Non-Chrome Primers**

- MIL-PRF-85582 Class N Primers

- Type I, EWDY048
 - Type II, EEAE118
 - 44-GN-098, Deft
- } PRC DeSoto

Qualified over a Chrome
Conversion Coating

- MIL-PRF-23377 Class N Primers

- 16798-TEP, Hentzen
 - 02-GN-083
 - 02-GN-084
- } Deft

Result: NO QUALIFIED COMPLETE NON-CHROME COATING SYSTEM
(Pretreatment/Primer/Topcoat)



Issues with Non-Chrome



Public Affairs release # 88ABW-2008-0909

- **Chrome Inhibitors are a Technology**
 - **Much Characterization before Specifications**
 - **Pretreatment MIL-PRF-81706**
 - **Primer MIL-PRF-23377 or MIL-PRF-85582**
 - **Topcoat MIL-PRF-85285**
 - **Robust could mix and match with little variance in performance**



Unclear Requirement




Public Affairs release # 88ABW-2008-0909

617-A1A-004

2000 hours Salt Spray
Complete Chrome System

MIL-DTL-81706
MIL-PRF-23377, Class C2
MIL-PRF-85285



MIL-DTL-81706
MIL-PRF-23377, Class C2
Deft APC



2024 T-3 Aluminum

617-A1B-005

2024 T-3 Aluminum



Unclear Requirement




Public Affairs release # 88ABW-2008-0909



4032 hours Salt Spray
Complete Chrome System

MIL-DTL-81706
MIL-PRF-23377, Class C2
MIL-PRF-85285



MIL-DTL-81706
MIL-PRF-23377, Class C2
Deft APC





Unclear Requirement



Public Affairs release # 88ABW-2008-0909

- **First Versions of MIL-C-23377**
 - No Salt Fog Test
 - Formula Specification – Specified Amount of Chrome
- **Blistering of MIL-C-23377**
 - Added Humidity Test
 - Added Salt Fog Test – 1000hrs
- **Acquisition Reform**
 - Push to go to Performance Specifications
 - Removed Specified Amount of Chrome Requirement
 - Salt Fog Test – 2000hrs
 - Engineering Rule of Thumb – Double Requirement



Unclear Requirement



Public Affairs release # 88ABW-2008-0909

- **Non-Chrome is NOT a Technology**
 - **Each Non-Chrome Coating System is a Technology**
 - New technologies require characterization, sub-system field test, full up field test, etc
 - Then specifications built around that technology
 - **But, that is not what happened**
 - If pass salt spray, 2000hrs, then good to go
 - Chrome Coating Specifications modified to include a type for Non-chrome
 - **Problems developed**
 - **Changing components** of the system yielded big differences
 - Success in **lab tests did not translate** to outdoor exposure
 - Some success with **JGAPP primers** on F-15 but failure on KC-135
 - Pre-existing corrosion on OML of KC-135



Results of Changing Components




Public Affairs release # 88ABW-2008-0909

633-A1A-003

3000 hours Salt Spray

MIL-DTL-81706
MIL-PRF-23377, Class C2
Deft APC

Complete Chrome
System



MIL-DTL-81706
Deft 02-GN-084
Deft APC

Non- Chrome Primer



633-A1C-001

2024 T-3 Aluminum

2024 T-3 Aluminum



Results of Changing Components




Public Affairs release # 88ABW-2008-0909

633-A1C-001

3000 hours Salt Spray

MIL-DTL-81706
Deft 02-GN-084
Deft APC

Non- Chrome Primer



PreKote
Deft 02-GN-084
Deft APC

Complete Non- Chrome
System



633-A1N-003

2024 T-3 Aluminum



Results of Changing Components




Public Affairs release # 88ABW-2008-0909

633-A1C-001

3000 hours Salt Spray

MIL-DTL-81706
Deft 02-GN-084
Deft APC

Non- Chrome Primer



BoeGel
Deft 02-GN-084
Deft APC

Complete Non- Chrome
System



633-A1I-003

Blisters in Field

2024 T-3 Aluminum

2024 T-3 Aluminum



Lab Results vs Real World




Public Affairs release # 88ABW-2008-0909

617-A1B-005

2000 hours Salt Spray

**MIL-DTL-81706
MIL-PRF-23377, Class C2
Deft APC**

**Complete Chrome
System**



**Alodine 5200
Sicopoxy 577-630
Deft APC**

**Complete Non- Chrome
System**



617-A1X-005

2024 T-3 Aluminum

2024 T-3 Aluminum






Lab Results vs Real World



Public Affairs release # 88ABW-2008-0909

Laboratory Salt Fog 2000 hrs



**Outdoor Exposure After 3+ Years At Daytona
(Failure <1 year)**



Alodine 5200
Sicopoxy 577-630
Deft 03GY310
(MIL-PRF-85285 Ty 1)




AFRL Chromium-free Coating Systems Integration Plan Efforts



Public Affairs release # 88ABW-2008-0909

“Sicopoxy” Flight Test with T-38 at Randolph AFB (2008-2009)

- ✓ Conduct a field test to evaluate the capabilities of the selected non-chrome coating system against the standard coating system

Chromium Control		Chromium-free	
PreKote (3 Step Process)		Brulin 815GD Cleaner	
		Alodine 5700 Non-chrome Conversion Coat	
MIL-PRF-23377 Primer Sherwin Williams E90-G-203		ANAC 577-630 Non-Chrome Primer	
Topcoats Deft MIL-PRF-85285 (03-GY-308 and 03-GY-277)			



AFRL Chromium-free Coating Systems Integration Plan Efforts



Public Affairs release # 88ABW-2008-0909

T-38, Randolph AFB (Sep 2008)

Control Side

Test Side



- ✓ Aircraft looked good - no visual difference between control and test side
- ✓ Dry film thicknesses (3.06 mils test side, 3.96 mils control side), color, and gloss were taken
- ✓ Witness panels with both processes were taken for laboratory testing

No difference between Chrome system and Non-Chrome system Sept 2010



Issues with JGAPP NCr

(Chrome can Arrest Existing Corrosion)



Public Affairs release # 88ABW-2008-0909

- **JGAPP – KC-135 Field Test**
 - Hickam AFB
 - Half & Half
 - Chrome/Non-Chrome



- **Corrosion in Center of Skins**
 - Existing Corrosion Pits
 - NCr Could NOT Prevent
- **Sent Back to Depot**
 - Out of Cycle = Big Dollars




AFRL Path Forward



Public Affairs release # 88ABW-2008-0909

- **Coating System Specification - MIL-PRF-32239 (Outer Moldline Only)**
 - Eliminates issues with mixing components of a coating system
- **Develop Better Laboratory Test Methods – 3 Prongs**
 - Better Salt Fog Cabinet – Include UV
 - Family of Test Coupons to Represent Aircraft Structures and Loads
 - Initial Focus is KC-46 Fuselage
 - Evaluation Techniques – NDI, Corrosion Modeling – Feeds ASIP Models





AFRL Path Forward



Public Affairs release # 88ABW-2008-0909

- **Under Secretary of Defense, Mr. Young Letter**
- **Defense Acquisition Regulations System, 48 CFR Parts 223 and 252**
- **Non-Chrome Characterization Effort – Need to Reduce Risk**
 - 9 Non-Chrome Coating Systems
 - Laboratory Testing to MIL-PRF-32239
 - Extensive Outdoor Exposure Testing
 - 2024 and 7075 Scribed Panels
 - Pre-Corroded Panels
 - Fresh Anodized Panels
 - C-5 Skins – Anodized, Partial Primer
 - Panels with Fasteners
 - Battelle Sensors
 - Sea Water Spray and Without – Overhang (3X)




Outdoor Exposure





Public Affairs release # 88ABW-2008-0909

Painted 2024 Al Panels After 3+ Years At Daytona




Prekote/
AE 2100/
85285 Ty IV AE 5000



Chrome Control
81706/
23377, CI C2/
85285 Ty I Deft 03GY310



Alodine 5200/
Sicopoxy/
85285 Ty I Deft 03GY310
(Failure <1 Year)






Outdoor Exposure



Public Affairs release # 88ABW-2008-0909

Galvanic Test Samples Exposed at Daytona

2024-T3 Al with Cd Plated Steel Screws
Proven Very Effective In Discriminating
Among Paint Systems and Quickly
Failures <1 Year



System 2; Prekote/AE 2100/85285 Ty IV AE 5000
NC/NC; 2 Years




System 4 5541/23377, CI C2/
85285 Ty I 03GY310 C/C; 2 Years




Outdoor Exposure



Public Affairs release # 88ABW-2008-0909




System 6 Prekote/Americoat/85285 Ty I
NC/NC; 2 Years



C130 Matrix; 5541/85582 CI N/85285 Ty IV
C/NC; 1 Year

NOTE: AE 2100 requires good conductivity with substrate.

AE 2100 **NOT** recommended over conversion coating.



C130 Matrix; 5541/AE 2100/85285 Ty IV
C/NC; 1 Year



Outdoor Exposure



Public Affairs release # 88ABW-2008-0909

KC-135 Upper Wing Skins; Painted and Scribed; 2+ Years ; Daytona



System 4; C/C/85285, Ty IV
Middle

System 5; Alodine 5200/Sicopoxy/85285,
Ty IV Lower



System 2; PreKote/AE 2100/85285, Ty IV
Upper

System 4; C/C/85285, Ty IV Lower




Outdoor Exposure



Public Affairs release # 88ABW-2008-0909

Magnified
view of
fasteners
(2+ Years)

System 2; PreKote/AE2100/85285, Ty IV Deft ELT



System 4; C/C/85285, Ty IV Deft ELT





Mg-Rich Implementation



Public Affairs release # 88ABW-2008-0909

- **Norwegian Air Force – Jan 2012**
 - Performed best of all non-chrome tested
 - Approved for use
- **Germany Approval – May 2012**
 - Specification TL8010-0046
 - Used on Tornado and P3-C Orion
- **Italian Air Force – July 2012**
 - 30 C-130 to be painted



First Norwegian C-130



Public Affairs release # 88ABW-2008-0909

After application of the
Aerodur 2100MgRp



C130 AMI "VEGA 58"
Completely Painted





C-130 Field Testing



Public Affairs release # 88ABW-2008-0909

- **5 Aircraft Scheduled**
 - **Complete coverage of aircraft with test coating**
 - **2 Complete**
 - **20 Aug 2011 -- WR-ALC – Elmendorf AI**
 - **PreKote/ANAC Aerodur 2100/ANAC Aerodur 5000**
 - **7 May 2012 -- WR-ALC – Hurlburt FI**
 - **RECC 1015 (DeOX)/RECC 3021 (Pretreat)/Deft 02-GN-093/Deft 99-GY-XXX ELT**



F-16 Field Testing



Public Affairs release # 88ABW-2008-0909

- **In Planning Stage**
- **5 Aircraft**
- **4 Test Coatings, 1 Control**
 - 4 - Pretreatments and Primers
 - 1 - 5541/23377
- **Standard F-16 Topcoat**
 - MIL-PRF-85285 Ty IV
- **Coatings Rotate to Different Locations**
- **Test Duration = PDM Cycle**
 - 6 Years

